

SORTIMENT

Normal-Sortiment Kalksandstein-Mauerwerk: Stein- und Mörtelbedarf

Wanddicke	Steinsorte Bezeichnung	Format L/B/H	Steinbedarf	Mörtelbedarf	Flächenmasse roh Normalstein
mm		mm	Stück/m ²	Liter/m ²	ca. kg/m ²
Mit Normalmörtel: Lagerfugen 10 mm, Stossfugen 10 mm					
100	K 10/6,5	250/100/65	51	36	210
	K 10/14	250/100/140	26	21	180
	K 10/19	250/100/190	19	17	150
120	K 12/6,5	250/120/65	51	43	250
	K 12/9	250/120/90	38	34	210
	K 12/14	250/120/140	26	25	210
	K 12/19	250/120/190	19	20	200
150	K 15/6,5	250/145/65	51	52	300
	K 15/9	250/145/90	38	41	240
	K 15 RE	250/145/140	26	64	292
	K 15/14	250/145/140	26	30	250/300*
	K 15/19	250/145/190	19	25	240
180	K 18/6,5	250/180/65	51	65	400
	K 18/9	250/180/90	38	50	310
	K 18/14	250/180/140	26	37	325/370*
	K 18/19	250/180/190	19	31	300
200	K 20/6,5	250/200/65	51	72	420
	K 20/9	250/200/90	38	56	340
	K 20/14	250/200/140	26	41	350
	K 20/19	250/200/190	19	34	340
250	K 12/14	250/120/140	51	72	430
	K 15/14	250/145/140	43	65	410
	K 18/14	250/180/140	35	59	410
	K 20/14	250/200/140	31	56	450

* Verwendung von Schallschutzsteinen (K 15 schwer, K 18 schwer)

Wanddicke	Steinsorte Bezeichnung	Format L/B/H	Steinbedarf	Mörtelbedarf	Flächenmasse roh Normalstein
mm		mm	Stück/m ²	Liter/m ²	ca. kg/m ²

Mit Dünnbettmörtel: Lagerfugen 2 mm, Stossfuge Knirsch (Nut und Kamm)

70	KSP 70	498/70/248	8	2,0	131
100	KSPE 100/248	373/100/248	10,7	1,4	139
115	KSPE 115/248	248/115/248	16	1,8	190
150	KSPE 150/248	248/150/248	16	1,8	248
175	KSPE 175/248	248/175/248	16	1,8	288
200	KSPE 200/248	248/200/248	16	2,0	368
240	KSPE 240/248	248/240/248	16	2,0	445
125	Fasen-/Normalstein	250/123/198	20	ca. 2,2	190
150	Fasen-/Normalstein	250/148/198	20	ca. 2,7	260